

PCT

WORLD INTELLECTUAL PRO  
International

INTERNATIONAL APPLICATION PUBLISHED UNDER

WO 9605810A1

(51) International Patent Classification 6 :

A61K 9/16, 9/00

A1

(11) International Publication Number:

WO 96/05810

(43) International Publication Date:

29 February 1996 (29.02.96)

(21) International Application Number: PCT/GB95/01980

(22) International Filing Date: 21 August 1995 (21.08.95)

(30) Priority Data:

9416884.6

20 August 1994 (20.08.94)

GB


(71) Applicant (for all designated States except US): DANBIOSYST  
UK LIMITED [GB/GB]; Albert Einstein Centre, Highfields  
Science Park, Nottingham NG7 2TN (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): WATTS, Peter, James  
[GB/GB]; Flat 2, 47 Highfield Road, West Bridgford,  
Nottingham NG2 6DR (GB). ILLUM, Lisbeth [DK/GB];  
19 Cavendish Crescent North, The Park, Nottingham NG7  
1BA (GB).(74) Agent: BASSETT, Richard; Eric Potter Clarkson, St. Mary's  
Court, St. Mary's Gate, Nottingham NG1 1LE (GB).(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH,  
CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE,  
KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK,  
MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI,  
SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent  
(AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW,  
SD, SZ, UG).

## Published

With international search report.

Before the expiration of the time limit for amending the  
claims and to be republished in the event of the receipt of  
amendments.(54) Title: DRUG DELIVERY COMPOSITION CONTAINING CHITOSAN OR DERIVATIVE THEREOF HAVING A DEFINED Z.  
POTENTIAL

## (57) Abstract

A drug delivery composition for administration to mucosa is provided. The composition comprises a pharmacologically active compound and particles, preferably powder or microspheres, of chitosan or a chitosan derivative or salt wherein the particles are either solidified or partially cross-linked such that they have a zeta-potential of +0.5 to +50 mV. Solidified particles are made by treating particles made from a water soluble chitosan salt with an alkaline agent such as sodium hydroxide in non-acid containing water to render them insoluble.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Drug delivery composition containing chitosan or derivative thereof having a defined z. potential

The present invention relates to drug delivery compositions and more particularly to compositions based on chitosan microparticles which  
5 provide for the improved uptake of active drug material across mucosal surfaces, such as the vagina, the small intestine, the colon, the lungs, the rectum, the eye, the buccal cavity or the nasal cavity.

A major problem in drug delivery is the effective absorption of polar  
10 molecules, that include high molecular weight material such as proteins and peptides, across biological membranes. Normally such molecules are not well taken up by the body if administered to the gastrointestinal tract, the buccal mucosa, the rectal mucosa, the vaginal mucosa or the intranasal mucosa. By a polar molecule, we mean a substance that has an  
15 octanol/water partition coefficient of less than 50. Recent studies with insulin have demonstrated that the absorption of such a compound can be increased if it is given together with a so-called absorption enhancer. These absorption enhancing materials have included surfactants of the non-ionic type as well as various bile salt derivatives. An increased  
20 permeability of membranes in the presence of these types of surfactant materials is obtained and the literature in the field of pharmaceutical sciences contains a wide range of such absorption promoters. (For a review see Davis *et al* (editors), *Delivery Systems for Peptide Drugs*, Plenum Press, New York, 1987). However, such materials are sometimes  
25 unacceptable because of their irritant effects on membranes. These include not only the non-ionic variety of surface active agents but also bile salts and bile salt derivatives (eg fusidic acid).

EP-A-023 359 and EP-A-122 023 describe a powdery pharmaceutical  
30 composition for application to the nasal mucosa and methods for

administration thereof. The pharmaceutical composition allows polypeptides and derivatives thereof to be effectively absorbed through the nasal mucosa. Similarly, US-A-4 226 849 describes a method for administering a powdery medicament to the nasal mucosa where the preferred composition has mucoadhesive properties.

Formulations based on microspheres for mucosal delivery have been described in WO 88/09163. The formulations contain certain enhancers to aid effective penetration of the mucosa by the drug. WO89/03207 further describes formulations which do not require an enhancer.

WO 90/09780 describes a composition consisting of a drug and a polycationic substance including chitosan that promotes the transport of the drug across mucosal membranes. The composition can also comprise microspheres of the polycationic substance.

Chitosan is deacetylated chitin, or poly-N-acetyl-D-glucosamine. It is available from Protan Laboratories, Inc. Redmond, Washington 98052, U.S.A. and, depending on the grade selected, can be soluble in water up to pH 6.0. Chitosan has previously been used to precipitate proteinaceous material, to make surgical sutures and as an immunostimulant. It has also been employed previously in oral drug formulations in order to improve the dissolution of poorly soluble drugs (Sawayanagi *et al*, *Chem. Pharm. Bull.*, 31, 1983, 2062-2068) or for the sustained release of drugs by a process of slow erosion from a hydrated compressed matrix (Nagai *et al* *Proc. Jt. US Jpn. Semin. Adv. Chitin. Chitosan. Relat. Enzymes*, 21-39. Zikakis J.P. (ed), Academic Press. Orlando (1984)).

Chitosan microspheres have been produced for use for example for enhanced chromatographic separation (Li Q. *et al*, *Biomater. Artif. Cells*

*Immobilization Biotechnol.* **21**, 1993, 391-8) for topical delivery of drugs (Machida Y, *Yakugaku Zasshi*, **113**, 1993, 356-68) for drug targeting after injection (Ohya Y *et al*, *J. Microencapsul.* **10**, 1993, 1-9) and for controlled release of drugs (Bodmeier R. *et al*, *Pharm Res.* **6**, 1989, 413-  
5 7, Chithambara *et al* *J. Pharm. Pharmacol.* **44**, 1992, 283-286).

EP 454044 and EP486959 describe polyelectrolyte microparticles or polysaccharide microspheres including chitosan microspheres for controlled slow release of drugs. The drug is chemically bound or  
10 adsorbed to the surface.

Glutaraldehyde cross linked chitosan microspheres have been described in JP 539149 (Taisho Pharm. Co.). The use of chitosan as a biodegradable polymer material that is then modified by an amphiphilic polymer and an  
15 agent modifying the interface properties has been described in EP 486959 (Vectorpharma).

The standard method for the preparation of non-dissolving chitosan microspheres or microcapsules is to use an emulsification method. For  
20 example Chithambara *et al* (Cross-linked chitosan microspheres preparation and evaluation as a matrix for controlled release of pharmaceuticals, *J. Pharm. Pharmacol.* **44**, 1992, 283-286) describe how an aqueous acetic acid dispersion of chitosan in paraffin oil using dioctylsulphosuccinate as a stabilising agent was cross-linked by  
25 glutaraldehyde. A similar emulsion cross-linking procedure was described by Hassan *et al* (Optimized formulation of magnetic chitosan microspheres containing the anticancer agent, oxantrazole, *Pharm. Research* **9**, 1992, 390). Microspheres made from the complexation of chitosan with other polymers but of opposite charge have been described in papers and patents  
30 (EP 454044 to Hoechst AG).

Ionotropic gelation of chitosan by tripolyphosphate has been reported by Bodmeier *et al* (*Pharm. Research* 6, 1989, 413). The chitosan beads so prepared disintegrated at acid pH.

- 5    Microspheres intended to be bioadhesive have been described by Mathiowitz *et al* in PCT/US/03822. The microspheres were characterised by having a bioadhesive force of at least 11 mN/cm<sup>2</sup> as measured in a tensile test in the rat intestine. The attachment of positively charged ligands to microspheres to improve adhesion due to the electrostatic  
10   attraction of the cationic groups coating the beads, to the net negative charge of the mucus is mentioned as a possible strategy. The preparation of chitosan microspheres is described. The particles were prepared using a 1% chitosan concentration at pH 5.0. They were cross-linked using tripolyphosphate (3%). The particles so prepared were apparently of a  
15   size of approximately 2000  $\mu$ m. It is noted that chitosan microparticles were found not to be satisfactory since the force of detachment per projected surface area (mN/cm<sup>2</sup>) for such particles was less than 5 mN/cm<sup>2</sup>.
- 20   We have now surprisingly found that positively charged solidified or partially cross-linked chitosan particles are able to considerably improve the absorption of drugs across mucosal tissue. They appear to do so by prolonging the known absorption promoting effect of the chitosan resulting in a sustained absorption. This is surprising since chitosan in solution  
25   gives rise to a pulsed absorption profile similar to the one obtained when using bioadhesive microspheres such as starch (WO 88/09163, WO 89/03207).

In one aspect, the invention therefore provides a drug delivery  
30   composition for administration to mucosa comprising a pharmacologically

active compound and particles of chitosan or a chitosan derivative or salt, wherein the particles are either solidified or partially cross-linked such that they have a zeta potential of +0.5 to +50mV.

- 5 Preferably the particles are either microspheres or powder.

The surface charge of the particles expressed as the zeta potential is determined at pH 7.4 and 0.1 M ionic strength.

- 10 The method by which the zeta potential is measured depends on the size of the particles. For particles of 5 $\mu$ m or more, the zeta potential is measured by microelectrophoresis using for example a Rank Mark II microelectrophoresis apparatus (Rank Bros., Cambridge). For particles below 5 $\mu$ m, the zeta potential is measured by Laser Doppler Anemometry  
15 (LDA) using for example a Malvern Zeta Sizer IV (Malvern, UK).

### Microelectrophoresis

- For microelectrophoretic studies, a Rank Mark II microelectrophoresis  
20 apparatus (Rank Bros., Cambridge) can be used. A cylindrical glass microelectrophoresis cell is placed in a thermostated water bath at 25°C. Platinum black electrodes, prepared by oxidation in platinum chloride, are placed at either end of the cell. Illumination is by a 40mW gas laser (Scientific and Cook Electronic, UK). The movement of the particles is  
25 viewed by means of a binocular microscope system.

- The inter-electrode distance is calculated by measuring the conductivity of standard solutions of potassium chloride of for example 0.10M and 0.01M ionic strength at 25°C. The specific conductivity is the reciprocal of the  
30 resistance of a 1m long and 1m<sup>2</sup> in cross-section column of solution

$$(ie) \ k = \frac{\ell}{\pi a^2 R}$$

where  $k$  is the conductivity,  $\ell$  the inter-electrode distance and  $R$  the  
5 resistance of the cell. The resistance is determined by measuring the  
change in current for a known change in voltage.

For the determination of the particle mobility the cell is filled with the  
appropriate buffer system (0.1M ionic strength, for example phosphate  
10 buffer or McIlvaine buffer, pH = 7.4) and 1% w/v of the particles  
suspended in the buffer.

The suspension is left to equilibrate at 25°C for 5 minutes before any  
measurements are taken. The electrodes are placed at each end of the cell  
15 to form a tight seal. A voltage in the range 20-60 volt is applied across  
the electrodes to give a reasonable transit time which reduces errors due  
to Brownian motion and operator timing. The velocity of individual  
particles is timed across a fixed distance, such as 30µm calculated from  
an eyepiece graticule. Alternative measurements are taken with the  
20 electrode polarity reversed to prevent electrode polarization. The velocity  
of fifteen particles in each direction and at two voltages are measured and  
the electrophoretic mobility ( $u$ ) calculated from

$$25 \quad u = \frac{V}{E}$$

where  $V$  is the particle velocity (µms<sup>-1</sup>). The electrophoretic mobilities  
can be converted to zeta potentials ( $\zeta$ ) using the equation derived by  
Smoluchowski (1903)

$$U = \frac{\epsilon \zeta}{4\pi\eta}$$

where  $\epsilon$  is the permittivity and  $\eta$  the viscosity of the dispersion medium.

- 5 Assumptions are made as to the values of  $\epsilon$  and  $\eta$  in the electrical double layer. As a guideline the zeta potential can be obtained from the electrophoretic mobility by multiplying by approximately 15.

### Laser Doppler Anemometry

10

Laser Doppler Anemometry involves the detection of scattered laser light from particles which are moving in an applied electric field. The equipment used can for example be a Malvern Zetasizer II (Malvern Instruments). The sample is illuminated with a laser light source (15mW  
15 Helium-Neon laser) which is split into two beams of equal intensity. The split beams are then forced to cross to give an ellipsoid measuring volume; consisting of dark and light bands. The interference fringe pattern will be dependent on the beam crossing angle and the laser frequency. Particles moving under the application of an electric field will scatter light from the  
20 incident beam. The frequency shift- the Doppler frequency,  $F_d$ - is a function of the particle velocity as described by

$$F_d = 2 \sin (\lambda\theta/2)u$$

- 25 where  $\theta$  is the detection angle,  $\lambda$  the laser wavelength and  $u$  the particle velocity, respectively. The Malvern instrument detects the scattered light intensity and converts this to a  $F_d$  and allows for the calculation of  $u$ . Particle velocities are usually expressed as electrophoretic mobilities. The electrophoretic mobility (EM) of a particle is defined as follows:-

30

$$EM = u / \text{field strength}$$

The zeta potential (ZP) can be calculated by application of the Smoluchowski equation since the measurements are to be carried out at  
5 low ionic strengths and with relatively large particles,

$$ZP = 4\eta u / e$$

where  $\eta$  is the viscosity of the medium,  $e$  is the dielectric constant and  $u$   
10 is the particle velocity, respectively.

Electrophoretic mobility measurements are carried out by dispersing microspheres in 10ml buffer solution such as phosphate or McIlvaine buffer from 100 $\mu$ g - 1mg, with a constant ionic strength 0.1M. Four  
15 readings are taken using a PC4 wide capillary cell at a voltage of 100 volt, electrode spacing of 50mm and a dielectric constant of 78.54.

By "solidified particles" we mean particles made from a water soluble salt of chitosan that has been made insoluble in non-acid containing water by  
20 exposure to an alkaline agent. Exposure to the alkaline agent brings the chitosan out of solution so that it is no longer in its soluble salt form. Suitable alkaline agents for use include sodium hydroxide, calcium hydroxide, aluminium hydroxide, potassium hydroxide, sodium phosphate, sodium carbonate and ammonia. Particles, either powder or  
25 microspheres, treated in this way still retain a positive charge. For example, solidified chitosan microspheres can be prepared by emulsifying a chitosan or chitosan derivative salt into soya oil or a similar organic medium and adding an alkaline agent such as sodium hydroxide that solidifies (precipitates) the chitosan during mixing. The resultant solid  
30 microspheres will be positively charged in an aqueous suspension since no

crosslinking has taken place.

If the particles are cross-linked, the degree of cross-linking must be such that the particles retain a positive charge in the range of +0.5 mV to +50 mV. If the particles are completely cross-linked and all available -NH<sub>2</sub> groups are used, they will become neutral or negatively charged. By partially cross-linking the chitosan, it is possible to leave the particles positively charged and partly soluble. The degree of cross-linking required is determined by measuring the zeta potential.

10

Partially crosslinked microspheres can be prepared using for example either emulsification or spray drying techniques. In the emulsification technique the chitosan solution is emulsified in an organic medium such as toluene or soya oil with an emulsifier such as Span 80. A crosslinking agent in the form of for example glutaraldehyde or formaldehyde is either added to the organic phase before mixing with the chitosan solution or can be added after emulsification has taken place. The partly crosslinked microspheres can be harvested by filtration and washing.

20 The chitosan microspheres can be prepared by spray drying a solution of chitosan (0.05% w/v - 0.5% at pH 3 - 7) containing an appropriate amount of glutaraldehyde or formaldehyde or similar crosslinking agent.

For obtaining positively charged chitosan microspheres the ratio of the crosslinking agent to chitosan should be 0.01 to 1.00 more preferably 0.05 to 0.75 and most preferably 0.1 to 0.6.

The zeta potential of the particles is preferably +1.0mV to 45mV and more preferably +1.5mV to +40mV, more preferably 2.0mV to 35mV and especially +3.0mV to +30mV.

30

The chitosan or chitosan derivative or salt used preferably has a molecular weight of 4 000 or more, preferably in the range 25 000 - 2 000 000 and most preferably about 50 000 - 300 000. Chitosan or salts of chitosan may be used.

5

We use the term chitosan derivatives to include ester, ether or other derivatives formed by interaction of acyl or alkyl groups with the OH groups and not the NH<sub>2</sub> groups. Examples are O-alkyl ethers of chitosan, O-acyl esters of chitosan. Suitable derivatives are given in G.A.E.

10 Roberts, Chitin Chemistry, MacMillan Press Ltd, London, 1992. Suitable salts of chitosan include nitrates, phosphates, sulphates, xanthates, hydrochlorides, glutamates, lactates, acetates.

15 The composition is preferably administered as a freeze dried formulation of the particles together with the active compound. The composition can also be prepared as a physical/mechanical mixture of the dried microspheres with the drug.

20 The microspheres may be prepared by spray drying, emulsification, solvent evaporation, precipitation or other methods known to a person skilled in the art. The active drug can be incorporated into the microspheres during their production or sorbed onto the microspheres after their production. The microspheres or powder can be partially cross-linked by glutaraldehyde, formaldehyde, benzydianone, benzoquinone, 25 tripolyphosphate or other cross-linking agents known to the person skilled in the art. The conditions for carrying out the cross-linking, such as the amount of cross-linking agent required, are determined by monitoring the zeta potential and adjusting the conditions until the required zeta potential is obtained.

30

The size of the cross-linked or solidified microspheres are 1 - 200  $\mu\text{m}$ , more preferably 1 - 100 $\mu\text{m}$ .

If desired, other materials may be included in the composition, for example absorption enhancers. Suitable absorption enhancers include phospholipids such as lysophosphatidylcholine, lysophosphatidylglycerol and generally those mentioned in WO 88/09163.

The term "pharmacologically active compound" includes drugs, genes (DNA) or gene constructs, vaccines and components thereof (for example isolated antigens or parts thereof) and monoclonal antibodies.

The compositions may be used with drugs selected from the following non-exclusive list: insulin, PTH (parathyroid hormone), PTH analogues, calcitonins (for example porcine, human, salmon, chicken or eel) and synthetic modifications thereof, enkephalins, LHRH (lutenising hormone releasing hormone) and analogues (nafarelin, buserelin, leuprolide, goserelin), glucagon, TRH (Thyrotrophine releasing hormone), Vasopressin, Desmopressin, growth hormone, heparins, GHRH (growth hormone releasing hormone), nifedipine, THF (thymic humoral factor), CGRP (calcitonin gene related peptide), atrial natriuretic peptide, metoclopramide, ergotamine, Pizotizin, vaccines (particularly AIDS vaccines, measles, rhinovirus Type 13 and respiratory syncytial virus, influenza vaccines, pertussis vaccines, meningococcal vaccines, tetanus vaccines, diphtheria vaccines, cholera vaccines, DNA vaccines), pentamidine and CCK (cholecystokinin).

Further drugs include: antibiotics and antimicrobial agents such as tetracycline hydrochloride, leucomycin, penicillin, penicillin derivatives, erythromycin, sulphathiazole and nitrofurazone; antimigraine compounds

such as sumatriptan or other 5-HT<sub>1</sub> agonists; vasoconstrictors such as phenylephrine hydrochloride, tetrahydrozoline hydrochloride, naphazoline nitrate, oxymetazoline hydrochloride and tramazoline hydrochloride; cardiotonics such as digitalis and digoxin; vasodilators such as nitroglycerine and papaverine hydrochloride; bone metabolism controlling agents such as vitamin D and active vitamin D<sub>3</sub>; sex hormones; hypotensives; sedatives; anti-tumor agents; steroidal anti-inflammatory agents such as hydro-cortisone, prednisone, fluticasone, prednisolone, triamcinolone, triamcinolone acetonide, dexamethasone, betamethasone, beclomethasone and beclomethasone dipropionate; non-steroidal anti-inflammatory agents such as acetaminophen, aspirin, aminopyrine, phenylbutazone, mefenamic acid, ibuprofen diclofenac sodium, indomethacin, colchicine and probenecid; enzymatic anti-inflammatory agents such as chymotrypsin and bromelain seratiopeptidase; anti-histaminic agents such as diphenhydramine hydrochloride, chlorpheniramine maleate and clemastine; antitussive-expectorants such as codeine phosphate and isoproterenol hydrochloride; analgesics such as morphine and its polar metabolites such as morphine-6-glucuronides and morphine-3-sulphate; antiemetics such as metoclopramide, ondansetron, chlorpromazine; drugs for treatment of epilepsy such as Clonazepam; drugs for treatment of sleeping disorders such as melatonin; drugs for treatment of asthma such as salbutamol.

The compositions can be administered via the nasal route as a powder using a nasal powder device, via the vaginal route as a powder using a powder device, formulated into a vaginal suppository or pessary or vaginal tablet or vaginal gel and via the pulmonary route using a powder inhaler or metered dose inhaler, via the rectal route formulated into suppositories and via the small intestine or colonic route formulated in tablets or capsules. The compositions may gel on the mucosa at least to some extent

Figure 7 shows the plasma calcium concentrations in sheep following the vaginal administration of salmon calcitonin (1600 IU) in a pessary containing cross-linked chitosan or as a solution;

Figure 8 shows the mean plasma glucose/time curve after administration to sheep of 2 IU/kg insulin in chitosan solution and as a freeze-dried chitosan/lactose powder;

Figure 9 shows the plasma concentration of LHRH agonist in sheep after intranasal and subcutaneous administration;

Figure 10 shows the plasma concentration of LHRH agonist in sheep after vaginal administration of formulations containing chitosan microspheres;

Figure 11 shows the plasma concentration of LMWH following administration of subcutaneous solution and nasal microsphere formulation; and

Figure 12 shows the plasma concentration of PTH analogue following nasal administration of two chitosan powder formulations to sheep.

### Example 1

Partially cross-linked microspheres were prepared as follows:

1 g of Span 80 was mixed into 200 ml of soya oil. The oil/Span mixture was divided into two; one half was heated to 120°C. Into the remaining 100 ml of oil/Span was emulsified (Silverson homogeniser, 7000 rpm/3 min) 5 ml of a 10% w/v aqueous solution of low viscosity chitosan hydrochloride (Sea Cure CL113, Pronova, Drammen, Norway). The emulsion was poured into the hot oil/Span mixture and stirred at 1500 rpm using an overhead stirrer. After 10 minutes, the oil/Span/chitosan mixture was transferred to an ice bath and allowed to cool <40°C while stirring

and this may facilitate retention of the composition on the mucosa.

A further aspect of the invention provides a method of treating a human or other mammal by administering a composition as described above to a mucosal surface of that human or other mammal, for example the vagina, rectum, lungs, eye, colon or nasal cavity.

Preferred embodiments of the invention will now be described by way of example and with reference to the figures in which:

10

Figure 1 shows the mean plasma glucose/time curves after administration to sheep of 2 IU/kg insulin in chitosan solution and with chitosan microspheres (prepared by emulsion heat method followed by formaldehyde treatment);

15

Figure 2 shows the mean plasma glucose/time curves after administration to sheep of 2 IU/kg insulin in chitosan solution and with chitosan microspheres (prepared by adding glutaraldehyde to chitosan emulsion);

20

Figure 3 shows the mean plasma glucose/time curve after administration to sheep of 2 IU/kg insulin in chitosan solution and with cross-linked chitosan powder;

Figure 4 shows the mean plasma glucose/time curves after administration to sheep of 2 IU/kg insulin in chitosan solution and with chitosan microspheres (prepared by precipitation with sodium hydroxide);

25

Figure 5 shows the mean plasma calcium concentrations after nasal administration to sheep of 20 IU/kg salmon calcitonin in chitosan solution and with cross-linked chitosan powder;

Figure 6 shows the plasma morphine concentrations following nasal administration of morphine HCl in chitosan solution or with cross-linked chitosan;

30

continued. 100 ml of acetone was added and the mixture centrifuged (2500 rpm/ 5 min). The microspheres were washed with acetone, collected by filtration and allowed to dry. The entire process was repeated until 800 mg of microspheres had been prepared. The microspheres were  
5 stirred into a mixture of 40 ml of acetone and 10 ml of 38% w/v formaldehyde solution. After 24 hours the microspheres were recovered by filtration and resuspended in 100 ml of acetone. After a further 24 hours, the microspheres were recovered by filtration and dried at room temperature. The size of the microspheres was in the range 1-50  $\mu\text{m}$ .

10

### Example 2

Partially cross-linked microspheres were prepared as follows:

15 To 200 ml of soya oil was added 1 g of Span 80. The oil was stirred using an overhead mixer at 1000 rpm and 0.5 ml of 25% aqueous glutaraldehyde was added. After stirring for 30 minutes, 10 ml of a 5% w/v aqueous solution of low viscosity chitosan hydrochloride (Sea Cure CL113, Pronova, Drammen, Norway) was added to the oil/glutaraldehyde  
20 emulsion. After stirring at 1000 rpm for a further 75 minutes, 200 ml of acetone was added to the emulsion. The mixture was then centrifuged (2500 rpm/5 min). The microsphere pellets were resuspended in acetone, recovered by filtration, rinsed with further acetone and dried at room temperature. The majority of the microspheres were in the size range 10-  
25 50  $\mu\text{m}$ .

### Example 3

Partially cross-linked powder was prepared as follows:

30

Into a beaker was weighed 1 g of chitosan hydrochloride (Sea Cure CL113) powder. To the chitosan powder was added 80 ml of acetone and 20 ml of formaldehyde solution (38% w/v in water/methanol). The beaker contents were stirred for 24 hours. The cross-linked chitosan powder was recovered by filtration, and suspended in 200 ml of acetone. After 24 hours, the chitosan was recovered by filtration and dried in an oven at 50°C for 48 hours. The mean particle size of the cross-linked powder was 20  $\mu\text{m}$ .

#### 10 Example 4

Solidified chitosan microspheres were prepared as follows

A 2% w/v aqueous solution of medium viscosity chitosan glutamate (Sea Cure +210) was prepared. 10 ml of chitosan solution was emulsified (8000 rpm/10 min) into 100 ml of soya oil. 100 ml of 10% w/v sodium hydroxide solution was added and stirring continued at 8000 rpm for 5 min. The mixture was then mixed with a magnetic stirrer bar for a further 30 min. The microspheres were collected by centrifugation and washed with petroleum ether, then ethanol, and finally hot distilled water. Microspheres of mean diameter 25  $\mu\text{m}$  were obtained with a surface charge of +3.7 mV.

#### Example 5

25

Partially cross-linked microspheres were prepared as follows:

A 3% w/v aqueous solution of medium viscosity chitosan glutamate (Sea Cure +210) was prepared. 10 ml of chitosan solution was emulsified (8000 rpm/2 min) into a mixture of 100 ml of toluene and 1 g of Span 85.

2 ml of 8% w/v glutaraldehyde solution was added and the emulsion left to gently mix, using a magnetic stirrer bar, for 12 hours. The microspheres were collected by filtration, washed with toluene, and then ethanol, and left to dry.

5

### Example 6

Partially cross-linked microspheres were prepared as follows:

- 10 250 ml of a solution of 0.2% w/v chitosan in 1% acetic acid was prepared. 2 ml of 4% glutaraldehyde solution was added and the solution was spray-dried (Lab-Plant SD 04 spray-drier) using a drying temperature of 160°C and a flow rate of 5-10 ml/min. Chitosan microspheres of 5 µm diameter and a zeta potential of +5.7 mV were obtained.

15

### Example 7

- 600 mg of microspheres prepared using the method described in Example 1 were weighed into a 100 ml volumetric flask. To the microspheres were  
20 added 30 ml of water and 10 ml of sodium insulin solution (60 IU/ml). The flask contents were swirled intermittently for 20 minutes and then frozen by immersing the flask into liquid nitrogen. The frozen contents were transferred to a freeze-drier and lyophilised. The lyophilised formulation was administered nasally to each of four sheep at an insulin  
25 dose of 2 IU/kg (equivalent to 2 mg/kg of chitosan microspheres). As a control, a solution of 200 IU/ml insulin in 5 mg/ml medium viscosity chitosan solution was administered intranasally at 2 IU/kg. Blood samples were taken and plasma glucose concentrations measured. The mean changes in plasma glucose concentration with time for the two  
30 formulations is shown in Figure 1. It can be seen that the fall in plasma

glucose was of greater magnitude and more prolonged with the microsphere formulation of the invention than with the chitosan solution.

#### Example 8

5

A lyophilised formulation containing insulin was prepared from 600 mg of the microspheres described in Example 2 using the method described in Example 7. The lyophilised formulation was administered nasally to each of four sheep at an insulin dose of 2 IU/kg (equivalent to 2 mg/kg of chitosan microspheres). The chitosan solution formulation described in Example 7 was also administered. Blood samples were taken and plasma glucose concentrations measured. The mean changes in plasma glucose with time for the two formulations are shown in Figure 2. Although the minimum glucose concentration achieved was similar for both formulations, the duration of action achieved with the microsphere formulation was significantly prolonged compared with the chitosan solution.

10  
15

#### Example 9

20

A lyophilised formulation containing insulin was prepared from 600 mg of the cross-linked powder described in Example 3 using the method described in Example 7. The lyophilised formulation was administered nasally to each of four sheep at an insulin dose of 2 IU/kg (equivalent to 2 mg/kg of chitosan powder). The chitosan solution formulation described in Example 7 was also administered. Blood samples were taken and plasma glucose concentrations measured. The mean changes in plasma glucose with time for the two formulations are shown in Figure 3. The fall in plasma glucose was of greater magnitude and more prolonged with the microsphere formulation of the invention compared with the chitosan

25  
30

solution.

### Example 10

5 A lyophilised formulation containing insulin was prepared from 600 mg of the microspheres described in Example 4 using the method described in Example 7. The lyophilised formulation was administered nasally to each of four sheep at an insulin dose of 2 IU/kg (equivalent to 2 mg/kg of chitosan microspheres). The chitosan solution formulation described  
10 in Example 7 was also administered. Blood samples were taken and plasma glucose concentrations measured. The mean changes in plasma glucose with time for the two formulations are shown in Figure 4.

### Example 11

15

Into a 100 ml conical flask was weighed 880 mg of the cross-linked powder described in Example 3. To the powder was added 53.7 ml of water and 5 ml of salmon calcitonin solution (1760 IU/ml). The flask contents were swirled intermittently for 20 minutes and then frozen by  
20 immersing the flask into liquid nitrogen. The frozen contents were transferred to a freeze-drier and lyophilised. The lyophilised formulation was administered nasally to four sheep at a salmon calcitonin dose of 20 IU/kg (equivalent to 2 mg/kg of chitosan powder). As a control, a solution of 2000 IU/ml salmon calcitonin in 5 mg/ml medium viscosity  
25 chitosan solution was administered intranasally at 20 IU/kg. Blood samples were taken and plasma calcium concentrations measured. The changes in plasma calcium concentration with time for the two formulations are shown in Figure 5. For the chitosan powder formulation, the fall in plasma calcium, indicative of calcitonin absorption, was  
30 markedly greater and more prolonged than for the chitosan liquid

formulation.

### Example 12

5 Into a 250 ml conical flask was weighed 800 mg of the cross-linked powder described in Example 3. To the powder was added 48.3 ml of water and 5 ml of 24 mg/ml morphine hydrochloride solution. The flask contents were swirled intermittently for 20 minutes and then frozen by immersing the flask into liquid nitrogen. A solution was prepared  
10 containing 30 mg/ml morphine hydrochloride in medium viscosity chitosan glutamate solution, adjusted to pH 4. The cross-linked chitosan powder and the chitosan liquid formulation were each dosed intranasally to a group of four sheep at a morphine hydrochloride dose of 0.3 mg/kg. Plasma samples were collected and analysed for morphine content using  
15 a radioimmunoassay. The concentration time curves for the two formulations are shown in Figure 6. The peak plasma concentration achieved was approximately 50% higher for the chitosan powder formulation than for the chitosan liquid formulation.

### 20 Example 13

Into a 500 ml conical flask was weighed 1400 mg of the cross-linked powder described in Example 3. To the powder was added 90 ml of water and 3.1 ml of salmon calcitonin solution (9000 IU/ml). The flask  
25 contents were swirled intermittently for 20 minutes and then frozen by immersing the flask into liquid nitrogen. The frozen contents were transferred to a freeze-drier and lyophilised. 18.54 g of Suppocire BS2X (Gattefosse) was weighed into a beaker and melted at 35°C. 0.36 g of the freeze-dried calcitonin/chitosan mixture was mixed into the melted  
30 Suppocire. The mixture was poured into each of four 5 g pessary moulds.

The pessaries were allowed to set, removed from the mould, and trimmed to a weight of 4.2 g. The pessaries were administered intravaginally to each of four sheep. An aqueous solution containing 1600 IU/ml of salmon calcitonin was also administered intravaginally to four sheep. The changes in plasma calcium concentration with time for the pessary formulation and aqueous solution are shown in Figure 7. The fall in plasma calcium, indicative of calcitonin absorption, was markedly greater in magnitude and duration for the pessary formulation than for the solution.

#### 10 Example 14

The effect of a chitosan solution formulation on the nasal absorption of insulin in sheep was compared with the effect of a chitosan powder formulation in which the chitosan had not been treated in any way. A solution of 200 IU/ml insulin in 5 mg/ml medium viscosity chitosan solution was administered intranasally at 2 IU/kg to sheep. The powder formulation was prepared by mixing 640 IU insulin with 80 mg chitosan HCl 211 and 720 mg lactose and administered to the sheep at 2 IU/kg. Blood samples were taken and plasma glucose concentrations measured. The mean changes in plasma glucose concentration with time for the two formulations is shown in Figure 8. The fall in plasma glucose was less pronounced for the powder formulation than for the chitosan solution.

#### Example 15

25

Into a 100 ml conical flask were weighed 640 mg of the microspheres described in Example 2. To the microspheres were added 26.7 ml of water and 16 ml of a solution containing 1 mg/ml of a LHRH agonist. The suspension was frozen and lyophilised. The lyophilised formulation was administered nasally to each of four sheep at a dose of 2.05 mg/kg

(= 0.05 mg/kg of LHRH agonist). As controls, four sheep received nasally, 0.05 mg/kg of LHRH agonist as an aqueous solution and four sheep received 0.01 mg/kg as a subcutaneous injection. Plasma samples were collected and the LHRH agonist content was measured using a radioimmunoassay. In Figure 9, the concentration vs. time profiles are shown for the microsphere formulation, the nasal solution and the subcutaneous injection. The microsphere formulation resulted in a marked enhancement in nasal absorption of the LHRH agonist. Compared to the subcutaneous injection, the mean bioavailabilities of the microsphere formulation and control solution were 1.5% and 36.6% respectively.

### Example 16

Into a 100 ml conical flask was weighed 640 mg of the microspheres described in Example 2. To the powder was added 26.7 ml of water and 16 ml of a solution containing 1 mg/ml of a LHRH agonist. 28 g of Suppocire BS2X (Gattefosse) was weighed into a beaker and melted at 35°C. 0.56 g of the freeze-dried LHRH/microsphere mixture was mixed into the melted Suppocire. The mixture was poured into each of five pessary moulds. The pessaries were allowed to set, removed from the mould, and trimmed to a weight of 4.2 g (= 2 mg of LHRH agonist/pessary). The pessaries were administered intravaginally to each of four sheep.

A gel formulation was prepared by suspending 0.6 g of the microspheres described in Example 2 in 10 ml of a solution containing 1.5 mg/ml LHRH agonist. 1.42 g of the gel formulation (= 2 mg of LHRH agonist) was administered to each of four sheep from two syringes (two 1 ml syringes, each containing 0.71 g of gel).

Four sheep were administered, intravaginally, 0.4 ml of a 5 mg/ml solution of LHRH agonist.

Plasma samples were collected and assayed for LHRH agonist content.

- 5 Plasma concentration vs. time profiles for the control solution and two vaginal formulations are shown in Figure 10.

The two formulations containing chitosan microspheres substantially enhanced the vaginal absorption of LHRH agonist. Compared to the subcutaneous control (Example 15), the bioavailabilities of the control solution, gel formulation and pessary formulation were 4.7%, 46.0% and 32.9% respectively.

#### Example 17

15

Into a 100 ml flask was weighed 640 mg of the microspheres described in Example 2. To the flask was added 27 ml of water and 16 ml of a 50 mg/ml aqueous solution of low molecular weight heparin (LMWH). The suspension was frozen and lyophilised. The lyophilised formulation was administered intranasally to four sheep at 4.5 mg/kg (= 2.5 mg/kg LMWH). As a control, four sheep received 1.25 mg/kg LMWH as a subcutaneous injection. Plasma samples were collected and the anti-factor Xa activity measured using a proprietary assay kit. By measuring the anti-factor Xa activity in standards containing known quantities of LMWH, the LMWH content of the sheep plasma samples was calculated. The plasma LMWH concentration vs. time profiles for the nasal and subcutaneous formulations are shown in Figure 11. Relative to the subcutaneous dose, the mean bioavailability of the nasal chitosan formulation was 19%.



### Example 18

Into a 100 ml flask was weighed 560 mg of the cross-linked chitosan powder described in Example 3. To the flask was added 37 ml of an aqueous solution containing 28 mg of a parathyroid hormone (PTH) analogue. The suspension was frozen and lyophilised. A physical mixture of cross-linked chitosan powder and PTH analogue was prepared by blending together 560 mg of cross-linked chitosan powder (Example 3) and 28 mg of PTH analogue. Blending was performed using a pestle and mortar. The two powder formulations were administered intranasally to four sheep at 2.1 mg/kg (= 0.1 mg/kg PTH analogue). As a control, four sheep received 0.01 mg/kg PTH analogue as an intravenous injection. Plasma samples were collected and the PTH analogue content measured using a radioimmunoassay technique. The plasma PTH analogue concentration vs. time profiles for the intravenous and two nasal and doses are shown in Figure 12. Relative to the intravenous dose, the mean bioavailabilities of the lyophilised and physical mixture formulations were 20.7% and 18.0% respectively.



## CLAIMS



1. A drug delivery composition for administration to mucosa comprising a pharmacologically active compound and particles of chitosan or a chitosan derivative or salt, wherein the particles are either solidified or partially cross-linked such that they have a zeta potential of +0.5 to +50mV, measured as herein defined.
2. A composition according to Claim 1 wherein the size of the chitosan particles is 1-100  $\mu\text{m}$ .
3. A composition according to claim 1 or 2 wherein the particles are either powder or microspheres.
4. A composition according to any one of claims 1-3 wherein the pharmacologically active compound is a peptide.
5. A composition according to Claim 4 wherein the pharmacologically active compound is insulin.
6. A composition according to Claim 4 wherein the pharmacologically active compound is calcitonin.
7. A composition according to Claim 4 wherein the pharmacologically active compound is PTH.
8. A composition according to any one of Claims 1-3 wherein the pharmacologically active compound is an antimigraine compound such as a 5HT<sub>1</sub> agonist.


9. A composition according to any one of Claims 1-3 wherein the pharmacologically active compound is morphine.
10. A composition according to any one of Claims 1-3 wherein the  
5 pharmacologically active compound is a polar molecule.
11. A composition according to any one of the preceding claims further comprising an absorption enhancing material.
- 10 12. A composition according to any one of the preceding claims wherein the composition is in a form suitable for administration to the mucosa of the nasal cavity, vagina, rectum, lungs, buccal cavity, eye, small intestine or colon.
- 15 13. A method of delivering a pharmacologically active compound across a mucosal surface comprising administering a composition comprising the pharmacologically active compound and particles of chitosan or a chitosan derivative or salt, wherein the particles are either solidified or partially cross-linked such that they have a zeta potential of  
20 +0.5 to +50mV, measured as herein defined.


**FIGURE 1****FIGURE 2**


2/9


**FIGURE 3****FIGURE 4**

**FIGURE 5****FIGURE 6**


**FIGURE 7**

**FIGURE 8**


**FIGURE 9**

**FIGURE 10**

8/9

**FIGURE 11**

9/9

**FIGURE 12**

## INTERNATIONAL SEARCH REPORT

national Application No

PCT/GB 95/01980

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 6 A61K9/16 A61K9/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,93 15737 (DANBIOSYST) 19 August 1993 see the whole document ---	1-13
A	WO,A,90 09780 (DANBIOSYST) 7 September 1990 cited in the application see the whole document -----	1-13

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*&\* document member of the same patent family

Date of the actual completion of the international search

7 December 1995

Date of mailing of the international search report

04.01.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax (+ 31-70) 340-3016

Authorized officer

Ventura Amat, A

# INTERNATIONAL SEARCH REPORT

national Application No  
PCT/GB 95/01980

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9315737	19-08-93	AU-B- 3458093	03-09-93
		EP-A- 0625044	23-11-94
		GB-A- 2277682	09-11-94
		JP-T- 7503481	13-04-95
		NO-A- 942787	27-07-94
-----			
WO-A-9009780	07-09-90	DE-D- 69008346	26-05-94
		DE-T- 69008346	25-08-94
		EP-A- 0460020	11-12-91
		ES-T- 2055904	01-09-94
-----			

